

Seam Welded Pipe (SSAW)						
Standard	Chemical					
	<u>Grade</u>	<u>C</u>	<u>Mn</u>	<u>Si</u>	<u>S</u>	<u>P</u>
AWWA C200-2017	St37/S235Jr	Max 0.17%	0.25-1.40	0.12-0.30	Max 0.035	Max 0.035